

PBL1Y

Code(d) **548457**

Code(e) **551455**

Refractive Index n_d	1.54814 1.548141	Abbe Number ν_d	45.73	Dispersion n_F-n_C	0.011986
Refractive Index n_e	1.550989	Abbe Number ν_e	45.45	Dispersion n_F-n_C	0.012123

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.51892
n_{1970}	1.97009	1.52371
n_{1530}	1.52958	1.52892
n_{1129}	1.12864	1.53374
n_t	1.01398	1.53542
n_s	0.85211	1.53845
$n_{A'}$	0.76819	1.54058
n_r	0.70652	1.54256
n_C	0.65627	1.54456
$n_{C'}$	0.64385	1.54513
$n_{\text{He-Ne}}$	0.6328	1.54566
n_D	0.58929	1.54804
n_d	0.58756	1.54814
n_e	0.54607	1.55099
n_F	0.48613	1.55655
$n_{F'}$	0.47999	1.55725
$n_{\text{He-Cd}}$	0.44157	1.56242
n_g	0.435835	1.56333
n_h	0.404656	1.56911
n_i	0.365015	1.57931
n_{334}	0.334148	1.59092
n_{326}	0.326106	1.59476

Constants of Dispersion Formula	
A_1	1.24772961E+00
A_2	1.01954909E-01
A_3	3.50479619E-01
B_1	9.26606623E-03
B_2	4.51754311E-02
B_3	4.50186705E+01

Chemical Properties	
Water Resistance(Powder) Group RW(P)	2
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	2
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	1.1

Mechanical Properties	
Young's Modulus E (10^8N/m^2)	613
Rigidity Modulus G (10^8N/m^2)	252
Poisson's Ratio σ	0.217
Knoop Hardness Hk[Class]	420 4
Abrasion Aa	124
Photoelastic Constant β (nm/cm/ 10^5Pa)	2.94

Temperature Coefficients of Refractive Index									
Range of Temperature (°C)	dn/dT relative ($10^{-6}/^\circ\text{C}$)								
	t	C'	He-Ne	D	e	F'	g	i	
-40~-20	1.2	1.6	1.7	1.8	2.0	2.5	3.0	4.5	
-20~ 0	1.2	1.7	1.7	1.9	2.1	2.6	3.1	4.7	
0~20	1.2	1.7	1.8	1.9	2.2	2.7	3.2	4.9	
20~40	1.3	1.8	1.8	2.0	2.2	2.8	3.3	5.0	
40~60	1.3	1.8	1.9	2.1	2.3	2.9	3.4	5.2	
60~80	1.3	1.9	1.9	2.1	2.4	2.9	3.5	5.4	

Partial Dispersions	
n_C-n_t	0.009141
$n_C-n_{A'}$	0.003985
n_d-n_C	0.003576
n_e-n_C	0.006424
n_g-n_d	0.015189
n_g-n_F	0.006779
n_h-n_g	0.005775
n_i-n_g	0.015976
n_C-n_t	0.009705
$n_e-n_{C'}$	0.005860
n_F-n_e	0.006263
n_i-n_F	0.022054

Relative Partial Dispersions	
$\theta_{C,t}$	0.7626
$\theta_{C,A'}$	0.3325
$\theta_{d,C}$	0.2983
$\theta_{e,C}$	0.5360
$\theta_{g,d}$	1.2672
$\theta_{g,F}$	0.5656
$\theta_{h,g}$	0.4818
$\theta_{i,g}$	1.3329
$\theta'_{C,t}$	0.8005
$\theta'_{e,C'}$	0.4834
$\theta'_{F,e}$	0.5166
$\theta'_{i,F'}$	1.8192

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0014
$\Delta\theta_{C,A'}$	0.0012
$\Delta\theta_{g,d}$	-0.0025
$\Delta\theta_{g,F}$	-0.0019
$\Delta\theta_{i,g}$	-0.0092

Thermal Properties	
Strain Point StP (°C)	361
Annealing Point AP (°C)	396
Transformation Temperature Tg (°C)	406
Yield Point At (°C)	453
Softening Point SP (°C)	567
Expansion Coefficients (-30~+70°C)	93
α ($10^{-7}/^\circ\text{C}$) (+100~+300°C)	106
Thermal Conductivity k (W/m·K)	0.951

Coloring			
λ_{80}	325	λ_5	305
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	320	$\lambda_{0.05}$	305

CCI		
B	G	R
0.00	0.00	0.00

Internal Transmittance		
$\lambda(\text{nm})$	τ 10mm	τ 25mm
240		
250		
260		
270		
280		
290		
300		
310	0.29	0.04
320	0.80	0.57
330	0.954	0.88
340	0.988	0.970
350	0.995	0.988
360	0.997	0.993
365	0.997	0.994
370	0.998	0.995
380	0.998	0.996
390	0.999	0.997
400	0.999	0.998
420	0.999	0.998
440	0.999	0.998
460	0.999	0.998
480	0.999	0.998
500	0.999	0.999
550	0.999	0.999
600	0.999	0.999
650	0.999	0.999
700	0.999	0.999
800	0.999	0.999
900	0.999	0.999
1000	0.999	0.999
1200	0.999	0.999
1400	0.998	0.996
1600	0.996	0.991
1800	0.983	0.958
2000	0.960	0.903
2200	0.919	0.81
2400	0.88	0.73

Other Properties	
Bubble Quality Group B	
Specific Gravity d	2.95
Remarks	

OHARA 17-04