

# S-BAM12

Code(d) **639449**

Code(e) **643446**

Refractive Index $n_d$	<b>1.63930</b> 1.639300	Abbe Number $\nu_d$	<b>44.87</b>	Dispersion $n_F-n_C$	<b>0.014247</b>
Refractive Index $n_e$	1.642684	Abbe Number $\nu_e$	44.59	Dispersion $n_F-n_C'$	0.014414

Refractive Indices		
$\lambda(\mu m)$		
$n_{2325}$	2.32542	1.60480
$n_{1970}$	1.97009	1.61040
$n_{1530}$	1.52958	1.61653
$n_{1129}$	1.12864	1.62223
$n_t$	1.01398	1.62422
$n_s$	0.85211	1.62781
$n_{A'}$	0.76819	1.63033
$n_r$	0.70652	1.63268
$n_C$	0.65627	1.63506
$n_{C'}$	0.64385	1.63573
$n_{He-Ne}$	0.6328	1.63635
$n_D$	0.58929	1.63917
$n_d$	0.58756	1.63930
$n_e$	0.54607	1.64268
$n_F$	0.48613	1.64930
$n_{F'}$	0.47999	1.65014
$n_{He-Cd}$	0.44157	1.65631
$n_g$	0.435835	1.65740
$n_h$	0.404656	1.66433
$n_i$	0.365015	1.67665

Constants of Dispersion Formula	
$A_1$	1.50161605E+00
$A_2$	1.26987445E-01
$A_3$	1.43544052E+00
$B_1$	9.40761826E-03
$B_2$	4.72602195E-02
$B_3$	1.41666499E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	2
Acid Resistance(Surface) Group SR	3.2
Phosphate Resistance PR	1.0

Mechanical Properties	
Young's Modulus E ( $10^9 N/m^2$ )	904
Rigidity Modulus G ( $10^8 N/m^2$ )	361
Poisson's Ratio $\sigma$	0.253
Knoop Hardness Hk[Class]	550   6
Abrasion Aa	144
Photoelastic Constant $\beta$ (nm/cm/ $10^9 Pa$ )	2.30

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	dn/dT relative ( $10^{-6}/°C$ )						
	t	C'	He-Ne	D	e	F'	g
-40~-20	2.3	2.6	2.7	2.8	3.0	3.5	4.1
-20~ 0	2.3	2.7	2.7	2.9	3.1	3.6	4.2
0~20	2.3	2.7	2.8	3.0	3.2	3.7	4.3
20~40	2.4	2.8	2.8	3.0	3.3	3.8	4.5
40~60	2.4	2.8	2.9	3.1	3.3	3.9	4.6
60~80	2.4	2.9	2.9	3.1	3.4	4.0	4.7

Partial Dispersions	
$n_C-n_t$	0.010836
$n_C-n_{A'}$	0.004725
$n_d-n_C$	0.004243
$n_e-n_C$	0.007627
$n_g-n_d$	0.018101
$n_g-n_F$	0.008097
$n_h-n_g$	0.006929
$n_i-n_g$	0.019244
$n_C-n_t$	0.011505
$n_e-n_{C'}$	0.006958
$n_F-n_e$	0.007456
$n_i-n_{F'}$	0.026505

Relative Partial Dispersions	
$\theta_{C,t}$	0.7606
$\theta_{C,A'}$	0.3316
$\theta_{d,C}$	0.2978
$\theta_{e,C}$	0.5353
$\theta_{g,d}$	1.2705
$\theta_{g,F}$	0.5683
$\theta_{h,g}$	0.4863
$\theta_{i,g}$	1.3507
$\theta'_{C,t}$	0.7982
$\theta'_{e,C'}$	0.4827
$\theta'_{F,e}$	0.5173
$\theta'_{i,F'}$	1.8388

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0034
$\Delta\theta_{C,A'}$	0.0014
$\Delta\theta_{g,d}$	-0.0010
$\Delta\theta_{g,F}$	-0.0006
$\Delta\theta_{i,g}$	0.0014

Thermal Properties	
Strain Point StP (°C)	565
Annealing Point AP (°C)	592
Transformation Temperature Tg (°C)	608
Yield Point At (°C)	645
Softening Point SP (°C)	717
Expansion Coefficients (-30~+70°C)	76
$\alpha$ ( $10^{-7}/°C$ ) (+100~+300°C)	91
Thermal Conductivity k (W/m·K)	0.954

Coloring			
$\lambda_{80}$	385	$\lambda_5$	345
$\lambda_{70}$			

Internal transmission			
$\lambda_{0.80}$	374	$\lambda_{0.05}$	348

CCI		
B	G	R
0.00	0.93	0.93

Internal Transmittance	
$\lambda(nm)$	$\tau$ 10mm
280	
290	
300	
310	
320	
330	
340	
350	0.13
360	0.49
370	0.75
380	0.87
390	0.928
400	0.955
420	0.977
440	0.983
460	0.987
480	0.990
500	0.993
550	0.997
600	0.996
650	0.996
700	0.997
800	0.998
900	0.998
1000	0.998
1200	0.998
1400	0.992
1600	0.995
1800	0.987
2000	0.976
2200	0.932
2400	0.86

Other Properties	
Bubble Quality Group B	
Specific Gravity d	3.18
Remarks	

OHARA 17-04