

# S-LAH99W

Code(d) **001291**

Code(e) **009289**

Refractive Index $n_d$	<b>2.00100</b> 2.001000	Abbe Number $\nu_d$	<b>29.14</b>	Dispersion $n_F-n_C$	<b>0.034352</b>
Refractive Index $n_e$	2.009118	Abbe Number $\nu_e$	28.92	Dispersion $n_F-n_{C'}$	0.034895

Refractive Indices		
$\lambda(\mu\text{m})$		
$n_{2325}$	2.32542	1.93863
$n_{1970}$	1.97009	1.94585
$n_{1530}$	1.52958	1.95440
$n_{1129}$	1.12864	1.96380
$n_t$	1.01398	1.96756
$n_s$	0.85211	1.97488
$n_{A'}$	0.76819	1.98035
$n_r$	0.70652	1.98561
$n_C$	0.65627	1.99105
$n_{C'}$	0.64385	1.99260
$n_{\text{He-Ne}}$	0.6328	1.99406
$n_D$	0.58929	2.00070
$n_d$	0.58756	2.00100
$n_e$	0.54607	2.00912
$n_F$	0.48613	2.02540
$n_{F'}$	0.47999	2.02749
$n_{\text{He-Cd}}$	0.44157	2.04319
$n_g$	0.435835	2.04600
$n_h$	0.404656	2.06424
$n_i$	0.365015	

Constants of Dispersion Formula	
$A_1$	2.39140662E+00
$A_2$	4.39219228E-01
$A_3$	2.38358467E+00
$B_1$	1.31467500E-02
$B_2$	5.53226042E-02
$B_3$	1.61259900E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	1
Acid Resistance(Surface) Group SR	2.0
Phosphate Resistance PR	1.0

Mechanical Properties	
Young's Modulus E (GPa)	131.3
Rigidity Modulus G (GPa)	50.2
Poisson's Ratio $\sigma$	0.307
Knoop Hardness Hk[Class]	720 * 7
Abrasion Aa	55

Partial Dispersions	
$n_C-n_t$	0.023490
$n_C-n_{A'}$	0.010695
$n_d-n_C$	0.009952
$n_e-n_C$	0.018070
$n_g-n_d$	0.045001
$n_g-n_F$	0.020601
$n_h-n_g$	0.018235
$n_i-n_g$	
$n_C-n_t$	0.025041
$n_e-n_{C'}$	0.016519
$n_{F'}-n_e$	0.018376
$n_i-n_{F'}$	

Relative Partial Dispersions	
$\theta_{C,t}$	0.6838
$\theta_{C,A'}$	0.3113
$\theta_{d,C}$	0.2897
$\theta_{e,C}$	0.5260
$\theta_{g,d}$	1.3100
$\theta_{g,F}$	0.5997
$\theta_{h,g}$	0.5308
$\theta_{i,g}$	
$\theta'_{C,t}$	0.7176
$\theta'_{e,C}$	0.4734
$\theta'_{F,e}$	0.5266
$\theta'_{i,F'}$	

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta \theta_{C,t}$	0.0004
$\Delta \theta_{C,A'}$	0.0001
$\Delta \theta_{g,d}$	0.0058
$\Delta \theta_{g,F}$	0.0054
$\Delta \theta_{i,g}$	

Thermal Properties	
Strain Point StP (°C)	682
Annealing Point AP (°C)	718
Transformation Temperature Tg (°C)	725
Yield Point At (°C)	761
Softening Point SP (°C)	792
Expansion Coefficients (-30~+70°C)	75
$\alpha$ ( $10^{-7} \text{K}^{-1}$ ) (+100~+300°C)	88
Thermal Conductivity $\lambda$ W/(m·K)	0.944

Coloring			
$\lambda_{80}$		$\lambda_5$	360
$\lambda_{70}$	405		

Internal transmission			
$\lambda_{0.80}$	393	$\lambda_{0.05}$	358

CCI		
B	G	R
0.00	2.83	2.98

Internal Transmittance	
$\lambda(\text{nm})$	$\tau$ 10mm
280	
290	
300	
310	
320	
330	
340	
350	
360	0.06
370	0.31
380	0.61
390	0.78
400	0.86
420	0.933
440	0.959
460	0.973
480	0.982
500	0.988
550	0.996
600	0.998
650	0.998
700	0.999
800	0.999
900	0.999
1000	0.999
1200	0.999
1400	0.999
1600	0.998
1800	0.992
2000	0.980
2200	0.955
2400	0.86

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n/\Delta T$ relative ( $10^{-6}\text{K}^{-1}$ )						
	t	C'	He-Ne	D	e	F'	g
-40~-20	2.1	3.4	3.5	3.9	4.5	5.8	7.4
-20~ 0	2.1	3.5	3.6	4.1	4.7	6.1	7.8
0~20	2.2	3.6	3.7	4.2	4.8	6.4	8.1
20~40	2.2	3.7	3.8	4.3	4.9	6.6	8.4
40~60	2.3	3.8	3.9	4.5	5.1	6.8	8.7
60~80	2.4	4.1	4.2	4.7	5.4	7.2	9.2

Other Properties	
Photoelastic Constant $\beta$ nm/(cm·10 <sup>5</sup> Pa)	0.76
Specific Gravity d	5.02
Remarks	

OHARA 23-05

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.