

# S-LAM54

Code(d) **757478**

Code(e) **761476**

Refractive Index $n_d$	<b>1.75700</b> 1.756998	Abbe Number $\nu_d$	<b>47.82</b>	Dispersion $n_F-n_C$	<b>0.015830</b>
Refractive Index $n_e$	1.760765	Abbe Number $\nu_e$	47.57	Dispersion $n_F-n_C'$	0.015991

Refractive Indices		
$\lambda(\mu\text{m})$		
$n_{2325}$	2.32542	1.71415
$n_{1970}$	1.97009	1.72188
$n_{1530}$	1.52958	1.73007
$n_{1129}$	1.12864	1.73729
$n_t$	1.01398	1.73970
$n_s$	0.85211	1.74394
$n_{A'}$	0.76819	1.74686
$n_r$	0.70652	1.74954
$n_C$	0.65627	1.75223
$n_{C'}$	0.64385	1.75299
$n_{\text{He-Ne}}$	0.6328	1.75370
$n_D$	0.58929	1.75686
$n_d$	0.58756	1.75700
$n_e$	0.54607	1.76076
$n_F$	0.48613	1.76806
$n_{F'}$	0.47999	1.76898
$n_{\text{He-Cd}}$	0.44157	1.77570
$n_g$	0.435835	1.77687
$n_h$	0.404656	1.78431
$n_i$	0.365015	1.79726

Constants of Dispersion Formula	
$A_1$	1.84213306E+00
$A_2$	1.75468631E-01
$A_3$	1.25750878E+00
$B_1$	9.43993220E-03
$B_2$	3.95281122E-02
$B_3$	8.65463013E+01

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	4
Weathering Resistance(Surface) Group W(S)	1~2
Acid Resistance(Surface) Group SR	51.0
Phosphate Resistance PR	2.0

Mechanical Properties	
Young's Modulus E ( $10^9\text{N/m}^2$ )	1172
Rigidity Modulus G ( $10^9\text{N/m}^2$ )	454
Poisson's Ratio $\sigma$	0.292
Knoop Hardness Hk[Class]	700   7
Abrasion Aa	69
Photoelastic Constant $\beta$ nm/(cm· $10^5\text{Pa}$ )	1.70

Partial Dispersions	
$n_C-n_t$	0.012530
$n_C-n_{A'}$	0.005376
$n_d-n_C$	0.004764
$n_e-n_C$	0.008531
$n_g-n_d$	0.019876
$n_g-n_F$	0.008810
$n_h-n_g$	0.007433
$n_i-n_g$	0.020388
$n_C-n_t$	0.013285
$n_e-n_{C'}$	0.007776
$n_F-n_e$	0.008215
$n_i-n_{F'}$	0.028282

Relative Partial Dispersions	
$\theta_{C,t}$	0.7915
$\theta_{C,A'}$	0.3396
$\theta_{d,C}$	0.3009
$\theta_{e,C}$	0.5389
$\theta_{g,d}$	1.2556
$\theta_{g,F}$	0.5565
$\theta_{h,g}$	0.4696
$\theta_{i,g}$	1.2879
$\theta'_{C,t}$	0.8308
$\theta'_{e,C'}$	0.4863
$\theta'_{F,e}$	0.5137
$\theta'_{i,F'}$	1.7686

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0205
$\Delta\theta_{C,A'}$	0.0058
$\Delta\theta_{g,d}$	-0.0098
$\Delta\theta_{g,F}$	-0.0076
$\Delta\theta_{i,g}$	-0.0367

Thermal Properties	
Strain Point StP (°C)	614
Annealing Point AP (°C)	637
Transformation Temperature Tg (°C)	664
Yield Point At (°C)	687
Softening Point SP (°C)	721
Expansion Coefficients (-30~+70°C)	57
$\alpha$ ( $10^{-7}/^\circ\text{C}$ ) (+100~+300°C)	69
Thermal Conductivity $\lambda$ W/(m·K)	0.891

Coloring			
$\lambda_{80}$	390	$\lambda_5$	340
$\lambda_{70}$			

Internal transmission			
$\lambda_{0.80}$	369	$\lambda_{0.05}$	340

CCI		
B	G	R
0.00	0.75	0.80

Internal Transmittance	
$\lambda(\text{nm})$	$\tau$ 10mm
280	
290	
300	
310	
320	
330	
340	0.05
350	0.33
360	0.65
370	0.82
380	0.909
390	0.945
400	0.963
420	0.979
440	0.985
460	0.990
480	0.993
500	0.995
550	0.997
600	0.997
650	0.998
700	0.998
800	0.999
900	0.998
1000	0.997
1200	0.997
1400	0.991
1600	0.991
1800	0.981
2000	0.954
2200	0.87
2400	0.62

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n/\Delta T$ relative ( $10^{-6}/^\circ\text{C}$ )						
	t	C'	He-Ne	D	e	F'	g
-40~-20	3.8	4.2	4.3	4.4	4.7	5.1	5.6
-20~ 0	4.0	4.4	4.5	4.7	4.9	5.4	5.9
0~20	4.2	4.7	4.7	4.9	5.1	5.6	6.2
20~40	4.4	4.9	4.9	5.1	5.3	5.9	6.4
40~60	4.5	5.1	5.1	5.3	5.6	6.1	6.7
60~80	4.7	5.3	5.3	5.5	5.8	6.4	7.0

Other Properties	
Bubble Quality Group B	
Specific Gravity d	4.08
Remarks	

OHARA 17-04

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.