

S-FPM 4

Code(d) **528765**

Code(e) **530760**

| | | | | | |
|------------------------|----------------------------|---------------------|--------------|-------------------------|-----------------|
| Refractive Index n_d | 1.52841 1.528410 | Abbe Number ν_d | 76.46 | Dispersion n_F-n_C | 0.006911 |
| Refractive Index n_e | 1.530060 | Abbe Number ν_e | 76.07 | Dispersion $n_F-n_{C'}$ | 0.006968 |

| Refractive Indices | | |
|------------------------|----------|---------|
| $\lambda(\mu\text{m})$ | | |
| n_{2325} | 2.32542 | 1.50911 |
| n_{1970} | 1.97009 | 1.51254 |
| n_{1530} | 1.52958 | 1.51625 |
| n_{1129} | 1.12864 | 1.51955 |
| n_t | 1.01398 | 1.52065 |
| n_s | 0.85211 | 1.52258 |
| $n_{A'}$ | 0.76819 | 1.52390 |
| n_r | 0.70652 | 1.52510 |
| n_C | 0.65627 | 1.52630 |
| $n_{C'}$ | 0.64385 | 1.52664 |
| $n_{\text{He-Ne}}$ | 0.6328 | 1.52695 |
| n_D | 0.58929 | 1.52835 |
| n_d | 0.58756 | 1.52841 |
| n_e | 0.54607 | 1.53006 |
| n_F | 0.48613 | 1.53321 |
| $n_{F'}$ | 0.47999 | 1.53361 |
| $n_{\text{He-Cd}}$ | 0.44157 | 1.53645 |
| n_g | 0.435835 | 1.53694 |
| n_h | 0.404656 | 1.54002 |
| n_i | 0.365015 | 1.54522 |

| Constants of Dispersion Formula | |
|---------------------------------|----------------|
| A_1 | 6.85585084E-01 |
| A_2 | 6.23380215E-01 |
| A_3 | 9.14178386E-01 |
| B_1 | 2.88172010E-03 |
| B_2 | 1.24701707E-02 |
| B_3 | 1.53577200E+02 |

| Chemical Properties | |
|---|------|
| Water Resistance(Powder) Group RW(P) | 1 |
| Acid Resistance(Powder) Group RA(P) | 3 |
| Weathering Resistance(Surface) Group W(S) | 1 |
| Acid Resistance(Surface) Group SR | 51.3 |
| Phosphate Resistance PR | 4.3 |

| Mechanical Properties | |
|--------------------------|---------|
| Young's Modulus E (GPa) | 74.7 |
| Rigidity Modulus G (GPa) | 28.9 |
| Poisson's Ratio σ | 0.295 |
| Knoop Hardness Hk(Class) | 380 4 |
| Abrasion Aa | 506 |

| Partial Dispersions | |
|---------------------|----------|
| n_C-n_t | 0.005650 |
| $n_C-n_{A'}$ | 0.002406 |
| n_d-n_C | 0.002107 |
| n_e-n_C | 0.003757 |
| n_g-n_d | 0.008533 |
| n_g-n_F | 0.003729 |
| n_h-n_g | 0.003076 |
| n_i-n_g | 0.008275 |
| n_C-n_t | 0.005985 |
| $n_e-n_{C'}$ | 0.003422 |
| $n_{F'}-n_e$ | 0.003546 |
| $n_i-n_{F'}$ | 0.011612 |

| Relative Partial Dispersions | |
|------------------------------|--------|
| $\theta_{C,t}$ | 0.8175 |
| $\theta_{C,A'}$ | 0.3481 |
| $\theta_{d,C}$ | 0.3049 |
| $\theta_{e,C}$ | 0.5436 |
| $\theta_{g,d}$ | 1.2347 |
| $\theta_{g,F}$ | 0.5396 |
| $\theta_{h,g}$ | 0.4451 |
| $\theta_{i,g}$ | 1.1974 |
| $\theta'_{C,t}$ | 0.8589 |
| $\theta'_{e,C'}$ | 0.4911 |
| $\theta'_{F',e}$ | 0.5089 |
| $\theta'_{i,F'}$ | 1.6665 |

| Deviation of Relative Dispersions $\Delta\theta$ from "Normal" | |
|--|---------|
| $\Delta\theta_{C,t}$ | -0.0879 |
| $\Delta\theta_{C,A'}$ | -0.0205 |
| $\Delta\theta_{g,d}$ | 0.0288 |
| $\Delta\theta_{g,F}$ | 0.0218 |
| $\Delta\theta_{i,g}$ | 0.1126 |

| Thermal Properties | |
|--|-------|
| Strain Point StP (°C) | - |
| Annealing Point AP (°C) | - |
| Transformation Temperature Tg (°C) | 488 |
| Yield Point At (°C) | 520 |
| Softening Point SP (°C) | - |
| Expansion Coefficients (-30~+70°C) | 123 |
| α (10 ⁻⁷ K ⁻¹) (+100~+300°C) | 143 |
| Thermal Conductivity λ W/(m·K) | 0.746 |

| Coloring | | | |
|----------------|-----|-------------|--|
| λ_{80} | 340 | λ_5 | |
| λ_{70} | | | |

| Internal transmission | | | |
|-----------------------|-----|------------------|-----|
| $\lambda_{0.80}$ | 335 | $\lambda_{0.05}$ | 283 |

| CCI | | |
|------|------|------|
| B | G | R |
| 0.00 | 0.14 | 0.11 |

| Internal Transmittance | |
|------------------------|-------------|
| $\lambda(\text{nm})$ | τ 10mm |
| 280 | 0.03 |
| 290 | 0.09 |
| 300 | 0.20 |
| 310 | 0.37 |
| 320 | 0.58 |
| 330 | 0.75 |
| 340 | 0.86 |
| 350 | 0.934 |
| 360 | 0.968 |
| 370 | 0.984 |
| 380 | 0.992 |
| 390 | 0.995 |
| 400 | 0.996 |
| 420 | 0.995 |
| 440 | 0.995 |
| 460 | 0.996 |
| 480 | 0.997 |
| 500 | 0.998 |
| 550 | 0.999 |
| 600 | 0.998 |
| 650 | 0.998 |
| 700 | 0.997 |
| 800 | 0.997 |
| 900 | 0.997 |
| 1000 | 0.997 |
| 1200 | 0.998 |
| 1400 | 0.999 |
| 1600 | 0.998 |
| 1800 | 0.998 |
| 2000 | 0.998 |
| 2200 | 0.996 |
| 2400 | 0.995 |

| Temperature Coefficients of Refractive Index | | | | | | | |
|--|--|------|-------|------|------|------|------|
| Range of Temperature (°C) | $\Delta n/\Delta T$ relative (10 ⁻⁶ K ⁻¹) | | | | | | |
| | t | C' | He-Ne | D | e | F' | g |
| -40~-20 | -5.4 | -5.2 | -5.2 | -5.1 | -5.0 | -4.9 | -4.7 |
| -20~ 0 | -5.7 | -5.5 | -5.5 | -5.5 | -5.4 | -5.2 | -5.0 |
| 0~20 | -5.9 | -5.8 | -5.8 | -5.7 | -5.6 | -5.4 | -5.2 |
| 20~40 | -6.2 | -6.0 | -6.0 | -5.9 | -5.8 | -5.6 | -5.4 |
| 40~60 | -6.3 | -6.1 | -6.1 | -6.1 | -6.0 | -5.8 | -5.6 |
| 60~80 | -6.4 | -6.2 | -6.2 | -6.1 | -6.1 | -5.9 | -5.6 |

| Other Properties | |
|--|------|
| Photoelastic Constant β nm/(cm·10 ⁵ Pa) | 0.72 |
| Specific Gravity d | 3.76 |
| Remarks | |

OHARA 24-01

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.