

S-FTM16

Code(d) **593353**

Code(e) **597350**

Refractive Index n_d	1.59270 1.592701	Abbe Number ν_d	35.31	Dispersion n_F-n_C	0.016785
Refractive Index n_e	1.596670	Abbe Number ν_e	35.03	Dispersion $n_F-n_{C'}$	0.017031

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.55603
n_{1970}	1.97009	1.56154
n_{1530}	1.52958	1.56767
n_{1129}	1.12864	1.57357
n_t	1.01398	1.57569
n_s	0.85211	1.57962
$n_{A'}$	0.76819	1.58243
n_r	0.70652	1.58508
n_C	0.65627	1.58779
$n_{C'}$	0.64385	1.58856
$n_{\text{He-Ne}}$	0.6328	1.58929
n_D	0.58929	1.59255
n_d	0.58756	1.59270
n_e	0.54607	1.59667
n_F	0.48613	1.60458
$n_{F'}$	0.47999	1.60559
$n_{\text{He-Cd}}$	0.44157	1.61318
n_g	0.435835	1.61454
n_h	0.404656	1.62334
n_i	0.365015	1.63974

Constants of Dispersion Formula	
A_1	1.32940907E+00
A_2	1.41512125E-01
A_3	1.44299068E+00
B_1	1.02377287E-02
B_2	5.78081956E-02
B_3	1.50597139E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	1~2
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	2.0

Mechanical Properties	
Young's Modulus E (GPa)	65.3
Rigidity Modulus G (GPa)	26.4
Poisson's Ratio σ	0.238
Knoop Hardness Hk(Class)	450 5
Abrasion Aa	181

Partial Dispersions	
n_C-n_t	0.012104
$n_C-n_{A'}$	0.005365
n_d-n_C	0.004906
n_e-n_C	0.008875
n_g-n_d	0.021838
n_g-n_F	0.009959
n_h-n_g	0.008800
n_i-n_g	0.025202
n_C-n_t	0.012872
$n_e-n_{C'}$	0.008107
$n_{F'-n_e}$	0.008924
$n_i-n_{F'}$	0.034147

Relative Partial Dispersions	
$\theta_{C,t}$	0.7211
$\theta_{C,A'}$	0.3196
$\theta_{d,C}$	0.2923
$\theta_{e,C}$	0.5287
$\theta_{g,d}$	1.3010
$\theta_{g,F}$	0.5933
$\theta_{h,g}$	0.5243
$\theta_{i,g}$	1.5015
$\theta'_{C,t}$	0.7558
$\theta'_{e,C'}$	0.4760
$\theta'_{F',e}$	0.5240
$\theta'_{i,F'}$	2.0050

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0088
$\Delta\theta_{C,A'}$	0.0010
$\Delta\theta_{g,d}$	0.0096
$\Delta\theta_{g,F}$	0.0090
$\Delta\theta_{i,g}$	0.0721

Thermal Properties	
Strain Point StP (°C)	-
Annealing Point AP (°C)	-
Transformation Temperature Tg (°C)	501
Yield Point At (°C)	542
Softening Point SP (°C)	-
Expansion Coefficients (-30~+70°C)	90
α (10 ⁻⁷ K ⁻¹) (+100~+300°C)	100
Thermal Conductivity λ W/(m·K)	0.947

Coloring			
λ_{80}	380	λ_5	350
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	370	$\lambda_{0.05}$	350

CCI		
B	G	R
0.00	0.43	0.42

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	
310	
320	
330	
340	
350	0.04
360	0.43
370	0.81
380	0.934
390	0.973
400	0.984
420	0.989
440	0.990
460	0.991
480	0.992
500	0.994
550	0.997
600	0.997
650	0.996
700	0.996
800	0.999
900	0.999
1000	0.999
1200	0.999
1400	0.996
1600	0.994
1800	0.989
2000	0.987
2200	0.959
2400	0.953

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n / \Delta T$ relative (10 ⁻⁶ K ⁻¹)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	-1.0	-0.5	-0.4	-0.2	0.0	0.7	1.4
-20~ 0	-0.9	-0.4	-0.3	0.0	0.2	0.8	1.6
0~20	-0.8	-0.2	-0.2	0.1	0.3	1.0	1.8
20~40	-0.7	-0.1	-0.1	0.2	0.5	1.2	2.1
40~60	-0.6	0.0	0.0	0.3	0.6	1.4	2.3
60~80	-0.5	0.1	0.1	0.4	0.7	1.6	2.5

Other Properties	
Photoelastic Constant β nm/(cm·10 ⁵ Pa)	3.33
Specific Gravity d	2.64
Remarks	

OHARA 24-01

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.