

S-TIM 5

Code(d) **603380**

Code(e) **607378**

Refractive Index n_d	1.60342 1.603420	Abbe Number ν_d	38.03	Dispersion n_F-n_C	0.015868
Refractive Index n_e	1.607179	Abbe Number ν_e	37.76	Dispersion $n_F-n_{C'}$	0.016082

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.56753
n_{1970}	1.97009	1.57306
n_{1530}	1.52958	1.57918
n_{1129}	1.12864	1.58500
n_t	1.01398	1.58708
n_s	0.85211	1.59089
$n_{A'}$	0.76819	1.59360
n_r	0.70652	1.59615
n_C	0.65627	1.59875
$n_{C'}$	0.64385	1.59948
$n_{\text{He-Ne}}$	0.6328	1.60017
n_D	0.58929	1.60328
n_d	0.58756	1.60342
n_e	0.54607	1.60718
n_F	0.48613	1.61462
$n_{F'}$	0.47999	1.61556
$n_{\text{He-Cd}}$	0.44157	1.62262
n_g	0.435835	1.62388
n_h	0.404656	1.63196
n_i	0.365015	1.64676

Constants of Dispersion Formula	
A_1	1.38531342E+00
A_2	1.22372945E-01
A_3	1.40508326E+00
B_1	1.04074567E-02
B_2	5.57440088E-02
B_3	1.44878733E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	2
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	1~2
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	1.2

Mechanical Properties	
Young's Modulus E (GPa)	76.3
Rigidity Modulus G (GPa)	30.9
Poisson's Ratio σ	0.233
Knoop Hardness Hk(Class)	540 5
Abrasion Aa	131

Partial Dispersions	
n_C-n_t	0.011667
$n_C-n_{A'}$	0.005143
n_d-n_C	0.004672
n_e-n_C	0.008431
n_g-n_d	0.020455
n_g-n_F	0.009259
n_h-n_g	0.008081
n_i-n_g	0.022880
n_C-n_t	0.012401
$n_e-n_{C'}$	0.007697
$n_{F'}-n_e$	0.008385
$n_i-n_{F'}$	0.031191

Relative Partial Dispersions	
$\theta_{C,t}$	0.7353
$\theta_{C,A'}$	0.3241
$\theta_{d,C}$	0.2944
$\theta_{e,C}$	0.5313
$\theta_{g,d}$	1.2891
$\theta_{g,F}$	0.5835
$\theta_{h,g}$	0.5093
$\theta_{i,g}$	1.4419
$\theta'_{C,t}$	0.7711
$\theta'_{e,C'}$	0.4786
$\theta'_{F',e}$	0.5214
$\theta'_{i,F'}$	1.9395

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0102
$\Delta\theta_{C,A'}$	0.0022
$\Delta\theta_{g,d}$	0.0034
$\Delta\theta_{g,F}$	0.0036
$\Delta\theta_{i,g}$	0.0353

Thermal Properties	
Strain Point StP (°C)	535
Annealing Point AP (°C)	565
Transformation Temperature Tg (°C)	588
Yield Point At (°C)	624
Softening Point SP (°C)	700
Expansion Coefficients (-30~+70°C)	83
α (10^{-7}K^{-1}) (+100~+300°C)	96
Thermal Conductivity λ W/(m·K)	1.04

Coloring			
λ_{80}	385	λ_5	350
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	378	$\lambda_{0.05}$	357

CCI		
B	G	R
0.00	0.79	0.81

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	
310	
320	
330	
340	
350	
360	0.19
370	0.60
380	0.84
390	0.931
400	0.963
420	0.984
440	0.989
460	0.991
480	0.993
500	0.995
550	0.997
600	0.997
650	0.997
700	0.997
800	0.999
900	0.998
1000	0.998
1200	0.998
1400	0.994
1600	0.994
1800	0.982
2000	0.966
2200	0.923
2400	0.902

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n / \Delta T$ relative (10^{-6}K^{-1})						
	t	C'	He-Ne	D	e	F'	g
-40~-20	1.4	1.9	1.9	2.1	2.4	3.0	3.7
-20~ 0	1.4	2.0	2.1	2.3	2.5	3.2	3.9
0~20	1.4	2.1	2.2	2.4	2.7	3.4	4.1
20~40	1.6	2.3	2.3	2.5	2.8	3.6	4.4
40~60	1.7	2.4	2.4	2.7	3.0	3.7	4.6
60~80	1.7	2.5	2.6	2.8	3.1	3.9	4.8

Other Properties	
Photoelastic Constant β nm/(cm·10 ⁵ Pa)	2.84
Specific Gravity d	2.63
Remarks	

OHARA 24-01

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.