

S-TIM 8

Code(d) **596392**

Code(e) **599390**

Refractive Index n_d	1.59551 1.595509	Abbe Number ν_d	39.24	Dispersion n_F-n_C	0.015176
Refractive Index n_e	1.599106	Abbe Number ν_e	38.97	Dispersion $n_F-n_{C'}$	0.015375

Refractive Indices		
$\lambda(\mu\text{m})$		
n_{2325}	2.32542	1.56075
n_{1970}	1.97009	1.56615
n_{1530}	1.52958	1.57212
n_{1129}	1.12864	1.57778
n_t	1.01398	1.57980
n_s	0.85211	1.58347
$n_{A'}$	0.76819	1.58609
n_r	0.70652	1.58854
n_C	0.65627	1.59103
$n_{C'}$	0.64385	1.59173
$n_{\text{He-Ne}}$	0.6328	1.59240
n_D	0.58929	1.59538
n_d	0.58756	1.59551
n_e	0.54607	1.59911
n_F	0.48613	1.60621
$n_{F'}$	0.47999	1.60711
$n_{\text{He-Cd}}$	0.44157	1.61382
n_g	0.435835	1.61501
n_h	0.404656	1.62267
n_i	0.365015	1.63661

Constants of Dispersion Formula	
A_1	1.37262713E+00
A_2	1.12636276E-01
A_3	1.39786421E+00
B_1	1.03220068E-02
B_2	5.50195044E-02
B_3	1.47735609E+02

Chemical Properties	
Water Resistance(Powder) Group RW(P)	1
Acid Resistance(Powder) Group RA(P)	1
Weathering Resistance(Surface) Group W(S)	2~3
Acid Resistance(Surface) Group SR	1.0
Phosphate Resistance PR	1.0

Mechanical Properties	
Young's Modulus E (GPa)	75.0
Rigidity Modulus G (GPa)	30.5
Poisson's Ratio σ	0.231
Knoop Hardness Hk(Class)	530 5
Abrasion Aa	135

Partial Dispersions	
n_C-n_t	0.011234
$n_C-n_{A'}$	0.004942
n_d-n_C	0.004479
n_e-n_C	0.008076
n_g-n_d	0.019504
n_g-n_F	0.008807
n_h-n_g	0.007657
n_i-n_g	0.021600
n_C-n_t	0.011938
$n_e-n_{C'}$	0.007372
$n_{F'}-n_e$	0.008003
$n_i-n_{F'}$	0.029504

Relative Partial Dispersions	
$\theta_{C,t}$	0.7402
$\theta_{C,A'}$	0.3256
$\theta_{d,C}$	0.2951
$\theta_{e,C}$	0.5322
$\theta_{g,d}$	1.2852
$\theta_{g,F}$	0.5803
$\theta_{h,g}$	0.5045
$\theta_{i,g}$	1.4233
$\theta'_{C,t}$	0.7765
$\theta'_{e,C'}$	0.4795
$\theta'_{F',e}$	0.5205
$\theta'_{i,F'}$	1.9190

Deviation of Relative Dispersions $\Delta\theta$ from "Normal"	
$\Delta\theta_{C,t}$	0.0094
$\Delta\theta_{C,A'}$	0.0022
$\Delta\theta_{g,d}$	0.0020
$\Delta\theta_{g,F}$	0.0023
$\Delta\theta_{i,g}$	0.0269

Thermal Properties	
Strain Point StP (°C)	529
Annealing Point AP (°C)	560
Transformation Temperature Tg (°C)	585
Yield Point At (°C)	610
Softening Point SP (°C)	695
Expansion Coefficients (-30~+70°C)	84
α (10 ⁻⁷ K ⁻¹) (+100~+300°C)	104
Thermal Conductivity λ W/(m·K)	1.03

Coloring			
λ_{80}	380	λ_5	350
λ_{70}			

Internal transmission			
$\lambda_{0.80}$	378	$\lambda_{0.05}$	351

CCI		
B	G	R
0.00	0.82	0.82

Internal Transmittance	
$\lambda(\text{nm})$	τ 10mm
280	
290	
300	
310	
320	
330	
340	
350	0.02
360	0.27
370	0.64
380	0.84
390	0.928
400	0.962
420	0.982
440	0.988
460	0.990
480	0.992
500	0.994
550	0.997
600	0.997
650	0.996
700	0.997
800	0.998
900	0.997
1000	0.996
1200	0.996
1400	0.994
1600	0.993
1800	0.983
2000	0.968
2200	0.935
2400	0.915

Temperature Coefficients of Refractive Index							
Range of Temperature (°C)	$\Delta n / \Delta T$ relative (10 ⁻⁶ K ⁻¹)						
	t	C'	He-Ne	D	e	F'	g
-40~-20	1.3	1.7	1.7	1.9	2.2	2.8	3.4
-20~ 0	1.3	1.8	1.8	2.0	2.3	2.9	3.5
0~20	1.3	1.8	1.9	2.1	2.3	3.0	3.7
20~40	1.4	1.9	1.9	2.1	2.4	3.1	3.8
40~60	1.4	1.9	2.0	2.2	2.5	3.2	4.0
60~80	1.5	2.0	2.0	2.3	2.6	3.3	4.1

Other Properties	
Photoelastic Constant β nm/(cm·10 ⁵ Pa)	2.79
Specific Gravity d	2.63
Remarks	

OHARA 24-01

OHARA Copyright© OHARA INC. All Rights Reserved.

※The name of the glass type is the model number assigned based on the main components of the composition: large, medium, small refractive index and serial number.